

Menovitá svetlosť		Vnútorý priemer	Hrúbka steny	Hmotnosť bez nátrubku
angl. "	DN	mm	mm	kg/m
3/8"	10	17,2	2,35	0,93
1/2"	15	21,3	2,65	1,27
3/4"	20	26,9	2,65	1,64
1"	25	33,7	3,25	2,52
1 1/4"	32	42,4	3,25	3,24
1 1/2"	40	48,3	3,25	3,72
2"	50	60,3	3,65	5,24
2 1/2"	65	76,1	3,65	6,69
3"	80	88,9	4,05	8,69
4"	100	114,3	4,50	

